



BISMALEIMIDE RESINS



Bismaleimide



o,o'-Diallyl bisphenol-A (DABA)

Lapox®	Appearance	Melting point	Viscosity ¹ @ 25°C	Purity	Recommendations
	–	°C	mPa · s	%	
ARBMI-11	Fine yellow powder	155 - 158	–	Min 95	A bismaleimide resin for composites, electrical and electronic applications. The product offers excellent thermal stability. CAS # 13676-54-5
ARD-63	Yellow to amber liquid	–	13,000 - 25,000	Min 85	A co-reactant (DABA) to use along with ARBMI-11. The product offers excellent processability and achieves high mechanical properties. CAS # 1745-89-7

¹Brookfield viscosity

*Method: Melting point - ASTM D2073; Viscosity - ASTM D2196