

BAKELITE® PF 9730**PRODUCT DESCRIPTION**

Water based phenolic resin solution.

Properties	Range			Unit	Method
Solid content	74	÷	77	%	TMP 5.01
Höppler viscosity 25°C	2,650	÷	3,150	mPas	10.017
pH 20°C	7,8	÷	8,2		10.019
Free phenol	5,0	÷	6,0	%	TMP 6.03

APPLICATION

This resin has been developed for the production of phenolic insulation foams. It allows to obtain very good and stable values of thermal conductivity.

PACKAGING

This product is delivered in:
- tank truck
- IBC.

SHELF LIFE AND STORAGE

This product has 14-21 days life if stored at 15°C.

SAFETY AND ENVIRONMENT

This product has to be used and disposed according to the indications given in its safety data sheet.

Reviewed on 09.11.2012

All data, instructions and recommendations presented herein are at the best of our knowledge true and accurate, but are only information. No guarantee is expressed and the user is entrusted to establish that the product utilisation does not infringe any existing patent. Our products are sold on condition that the user determines in advance their suitability for his own purposes.

Momentive Specialty Chemicals GmbH
Gennaer Str. 2 - 4
58642 Iserlohn (Germany)
Germany
Tel. (+49) (02374) 925 -322
Fax.:(+49) (2374) 925-336
Internet: www.momentive.com