

BAKELITE® PF 9810 PS**PRODUCT DESCRIPTION**

Water based phenolic resin solution.

Properties	Range			Unit	Method
Solid content	73,5	÷	76,0	%	TMP 5.01
Höppler viscosity 20°C	650	÷	800	mPas	10.017
Free phenol	2,5	÷	4,9	%	TMP 6.03
pH 20°C	5,9	÷	6,3		10.019

APPLICATION

This resin has been developed for the production of phenolic foams.

PACKAGINGThis product is delivered in:
- tank truck
- IBC.**SHELF LIFE AND STORAGE**

This product should be stored at 5-10°C.

SAFETY AND ENVIRONMENT

This product has to be used and disposed according to the indications given in its safety data sheet.

Reviewed on 08.02.2013

All data, instructions and recommendations presented herein are at the best of our knowledge true and accurate, but are only information. No guarantee is expressed and the user is entrusted to establish that the product utilisation does not infringe any existing patent. Our products are sold on condition that the user determines in advance their suitability for his own purposes.

Momentive Specialty Chemicals GmbH
Gennaer Str. 2 - 4
58642 Iserlohn (Germany)
Germany
Tel. (+49) (02374) 925 -322
Fax.:(+49) (2374) 925-336
Internet: www.momentive.com