

CELLOBOND J2027X

Cellobond J2027X is an unmodified liquid phenolic resole resin.

TYPICAL PROPERTIES

<u>PROPERTY</u>	<u>Value</u>
Viscosity at 25°C	150 – 220 cS
Specific gravity at 25°C	1.220 - 1.230 g/ml
Free Formaldehyde	1.0% max
pH	7.0 - 7.6
Water content	14.0 - 16.0%
Free phenol	< 10%
Pot Life	5 – 8 mins
Storage life	3 months

HEALTH AND SAFETY

Please read the relevant Material Safety Data Sheet CAREFULLY.

This material should be stored and handled in accordance with good industrial hygiene and safety practices.

www.Hexion.com

The information provided herein was believed by Hexion Inc. and its affiliated companies ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

© 2015 Hexion Inc. All rights reserved.
® and ™ denote trademarks owned or licensed by Hexion Inc.