Technical data sheet

Data of last alteration: 2019-08-01



#### Product information

# LT-171

Vinyl tri methoxy silane

#### **Product description**

Structural formula:

Empirical formula: C<sub>5</sub>H<sub>12</sub>O<sub>3</sub>Si

Molecular weight: 148.2 CAS No.: 2768-02-7

Chemical name: Vinyltrimethoxysilane

#### **Properties**

LT-171 is a bifunctional silane possessing a reactive vinyl group and a hydrolysable inorganic methoxysilyl group. The dual nature of its reactivity allows it to bind chemically to both inorganic materials (e.g. glass, metals, fillers) and organic polymers (e.g. thermoplastics, thermosets or elastomers), thus functioning as adhesion promoter, crosslinker, and/or surface modifier. LT-171 may also be useful as a moisture scavenger in moisture cure systems where enchanced shelf-life is sought.

Pipes and cables produced from silanecrosslinked polyethylene (PE) using LT-171 are more resistant to heat and weathering than products made from non-crosslinked PE. They also have improved electrical properties. The storage stability is greatly enhanced in formulations of silane-crosslinking adhesives and sealants. Use of LT-171 as a co-monomer

in polymer dispersions results in binders which exhibit much improved wet scrub resistance and higher abrasion resistance thanks to crosslinking and improved adhesion to the substrate.

It's a clear, colorless, low viscosity liquid with a typical aromatic odor. The silane hydrolyzes in the presence of moisture (methanol is released) to form silanols, which can then react with themselves to produce siloxanes.

### **Technical data**

Typical characteristics	Value
Appearance	Colorless liquid
Purity	≥99.0%
Density at 25 ℃	0.97g/ml
Boiling point at 760mmHg	123℃
Flash point, Tag closed cup	25℃
Refractive index (25°C)	1.3930

Note: the above data are for reference only, can not be used as a technical specification

#### Reactivity

In the presence of moisture the methoxy (Si-OCH<sub>3</sub>) groups of LT-171 hydrolyze to produce methanol and reactive silanol (Si-OH) groups which can bond to a variety of inorganic substrates or react with each other to form siloxane bonds (Si-O-Si). The organophilic vinyl end of LT-171 can also react with a suitable polymer initiated by peroxide.

## **Application and performance**

#### **NEW BLUESKY**

Technical data sheet

Data of last alteration: 2019-08-01



#### Moisture curing of polymers

LT-171 is suitable for the preparation of moisture-curing polymers, e.g. polyethylene. The characteristic feature of this process is peroxide-initiated grafting of the vinylsilane to the polymer during extrusion. After grafting. the polymer can still be processed as a thermo- plastics. Only upon treatment with moisture (in an 80-100 °C waterbath. steambath, or even at ambient conditions), the polymer chains are linked together; Thereby forming a crosslinked polymer. This reaction can be accelerated by using a catalyst. Silane cross- linked polyethylene is widely used as cable isolation, and sheathing mainly in low voltage applications as well as for hot water/sanitary pipes and underfloor heating. Heat resistance is the main reason for the crosslinking of polymers for cable applications, but crosslinking can also improve the following properties: tear- and crack resistance, chemical resistance, abrasion resistance, memory effect. LT-171 may also be used as a co-monomer for the preparation of different polymers such as polyethylene or acrylics. Those polymers show an improved adhesion to inorganic surfaces and they can also be crosslinked with moisture as described above.

# Adhesion promotion and surface modification

Because of its ability to react with inorganic fillers as well as with organic polymers (activated by e.g. peroxides or radiation), LT-171 acts as an efficient adhesion promoter for various mineral-filled polymers, improving mechanical and electrical after exposure to properties especially moisture. Once bonded to inorganic filler,

improving the compatibility of fillers with polymer, leading to a better dispersibility, reduced melt viscosity and easier processing of filled plastics. The pretreatment of glass, metals, or ceramic surfaces with LT-171 improves the adhesion of coatings on these surfaces and can thus improve the corrosion resistance.

#### As co-monomer for polymer dispersions

Polymer dispersions (e.g. styrene acrylics), modified with LT-171 show improved adhesion strength in wet conditions and wet scrub resistance.

#### As moisture scavenger

The electron withdrawing effect imparted by the silanes vinyl functionality enhances the rate of hydrolysis. This increased reactivity makes LT-171 silane one of the fastest hydrolyzing alkoxy silanes available. The elevated rate of hydrolysis is sufficient to enable LT-171 silane to be utilized as a moisture scavenging agent in moisture sensitive systems.

LT-171 silane can be incorporated into urethane, silylated polyurethane (SPUR prepolymer) or other silane modified polymer based sealants and adhesives to extend the systems shelf-life.

#### Other applications of LT-171

LT-171 can easily bond to OH-groups. Hydroxyl containing polymers e.g. functionalized silicones, may be modified with LT-171, thereby introducing reactive vinyl groups into the polymer chains. The vinyl group of LT-171 is activated by its proximity to silicon, which makes it an attractive molecule for different organic syntheses.

LT-171 hydrophobates the filler surface,

Product safety, handling and storage

# **NEW BLUESKY**

Technical data sheet

Data of last alteration: 2019-08-01



Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage condition required. The "Best use before end" date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Information on available container sizes is obtainable from **NEW BLUESKY** supplier.

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.

Hubei New Bluesky New Material Inc.

No.8, Xiacha, Industrial Park Development Road, Xiantao, Hubei, CHINA 433003

Telephone & Fax: +86-728-3254088; +86-728-3253808

 $\label{lem:email:essilanes} E-mail: cssilanes@blueskychemical.com \\ Website: \begin{tabular}{ll} www.blueskychemical.com \\ . \end{tabular}$ 

#### **Packaging**